



C/SIB	
	Y13



# SOLO

## SINGLE PART RAPID HARDENING HIGH PERFORMANCE LEVELLING COMPOUND.

Suitable for levelling floors prior to laying ceramic tiles, natural stone or sheet and tile, soft floor coverings.  
Bed thickness feather edge to 5mm: just add water.  
Bed thickness feather edge 5mm to 20mm: add equal volume of 3mm granite chippings

### SUITABILITY

Can be used to level a wide variety of absorbent and non-absorbent floor surfaces including concrete, sand/cement, terrazzo, asphalt, quarry tiles and old but sound adhesive residues.

### SURFACE PREPARATION

Surface must be dry and free from grease, oil, dirt and other contaminants. Sub-floors must incorporate a damp proof membrane. Sand/cement screeds must be fully cured and free from any surface hardeners. Apply acrylic bonding and priming agent to dry porous surfaces. Use neat on anhydrite screeds.

### UNGLAZED TILES, QUARRY TILES, TERRAZZO AND NATURAL STONE

Tiles should be firmly adhered. Loose or defective tiles must be removed.

### UNDER FLOOR HEATING

Heating must be switched off and floor allowed to cool to ambient temperature. Allow 48 hours for product to set and cure before switching back on.

### TIMBER FLOORS

Sheets and boards must be dry and firmly fixed and ventilated underneath. Apply Granfix acrylic bonding and priming agent and allow to dry (1 hour approx) before applying 'Solo'.

### OLD ADHESIVE RESIDUES

Remove as much as possible. Remaining adhesive must be firmly adhered. Apply Granfix acrylic bonding and priming agent prior to levelling.

### MIXING INSTRUCTIONS

Add powder to water until a smooth pourable product is obtained. Mixing ration 25kgs powder to 5 litres water. Use immediately. Spread product to required depth using a trowel. Above 5mm thickness incorporate an equal volume of granite chippings. Trowel marks should be rubbed out before laying soft floor coverings.

<b>COVERAGE</b>	25kgs will cover 5 square metres at 3mm bed thickness, 1.6kgs per square metre	
<b>STORAGE AND SHELF LIFE</b>	12 months minimum when stored in cool dry conditions	
<b>PACKAGING</b>	12.5kg and 25kg sacks	
<b>TECHNICAL DATA</b>	Product type	Polymer modified cementitious rapid setting pourable floor levelling compound
<b>APPLICATION TEMPERATURE</b>	Application temperatures	Between 5°C and 30°C
	Service conditions	-20°C to 150°C
	Pot life	40 mins at 20°C
	Initial set	2 hours at 20°C
	Light foot traffic	5 hours
	Full use	24 hours

**CODE OF PRACTICE** Wall and floor tiling should be carried out in accordance with BS 5385.

**NOTES**

The information and advice given is without prejudice and in good faith, and is believed to be accurate and complete.

The quality and consistency of Granfix Products are guaranteed. We have, however, no control over site conditions or the quality of workmanship. We accept no liability for any direct or indirect consequential loss or damages arising or resulting from the use of this information.

Timber subfloors should have been installed according to manufacturers instructions and relevant British standards particularly with regard to on-site ambient conditions.

# GRANFIX PRODUCTS LTD

RIDDINGS, ALFRETON, DERBY DE55 4AT

TELEPHONE: 01773 607778 FAX: 01773 608688 [www.tileadhesive.co.uk](http://www.tileadhesive.co.uk)